

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”


IS 5871 (1987): bitumen mastic for tanking and damp-proofing_ [CED 41: Waterproofing and Damp-Proofing]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



Indian Standard

SPECIFICATION FOR
BITUMEN MASTIC FOR TANKING AND
DAMP-PROOFING

(*First Revision*)

First Reprint AUGUST 1995

UDC 691.167:699.82

© Copyright 1988

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

Indian Standard

SPECIFICATION FOR BITUMEN MASTIC FOR TANKING AND DAMP-PROOFING

(*First Revision*)

Waterproofing and Damp-proofing Sectional Committee, BDC 41

Chairman

PROF M. S. SHETTY

Representing

Ministry of Defence (Engineer-in-Chief's Branch)

Members

LT-COL V. K. KANITKAR (<i>Alternate to</i> Prof M. S. Shetty)	
SRI R. C. ABORA	Hindustan Petroleum Corporation Ltd, Bombay
SRI N. VEERABANDHU	Central Public Works Department, New Delhi
SURVEYOR OF WORKS (NZ) (<i>Alternate</i>)	
SRI T. CHOUDHURY	National Test House, Calcutta
SRI D. S. GHUMMAN	Roofrite Private Limited, New Delhi
SRI K. K. LAL (<i>Alternate</i>)	
SRI A. D. GUPTA	Fertilizer (Planning and Development) India Limited, Sindri
SRI S. S. DAS GUPTA	Indian Oil Corporation Ltd, Bombay
SRI M. S. GUPTA	Roof Water proofing Company, Calcutta
SRI S. N. DUTTA GUPTA	Bharat Petroleum Corporation Ltd, Bombay
SRI A. D. NAYAK (<i>Alternate</i>)	
SRI S. K. JAIN	Hoechst Dyes and Chemicals Ltd, Bombay
SRI K. A. T. VAROHESE (<i>Alternate</i>)	
SRI M. B. JAYWANT	Synthetic Asphalts, Bombay
SRI S. K. KARAMOHANDANI	Union Carbide India Ltd, Calcutta
SRI V. NIJHAVAN (<i>Alternate</i>)	
SRI M. R. MALYA	In personal capacity (Flat No. 3, Panorama, 30 Pali Hill Road, Bombay)
SRI S. P. MODI	Engineers India Limited, New Delhi
DR MOHD ASLAM	Central Building Research Institute (CSIR), Roorkee
SRI M. V. PANSE	Public Works Department, Government of Maharashtra, Bombay

(Continued on page 2)

© Copyright 1988

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 5871 - 1987

(Continued from page 1)

Members

SHRI R. P. PUNJ	Lloyd Bitumen Products, Calcutta
SHRI M. M. MATHAI (Alternate)	
SHRI T. K. ROY	Shalimar Tar Products (1935) Ltd, Calcutta
SHRI B. K. BHATTACHARYA (Alternate)	
SHRI A. SEN GUPTA	Ministry of Railways, Calcutta
SENIOR DEPUTY CHIEF ENGINEER	Public Works Department, Government of
(BUILDING)	Tamil Nadu, Madras
SUPERINTENDING ENGINEER,	
DESIGN CIRCLE (Alternate)	
CAPT ASHOK SHASTRY	Onsar Chemical Pvt Ltd, Bombay
SHRI S. K. BANERJEE (Alternate)	
SHRI A. SHARIF	FGP Limited, Bombay
SHRI G. K. TAKIAR (Alternate)	
SHRI Y. S. SRINIVASAN	National Buildings Organization, New Delhi
SHRI SHASHI KANT (Alternate)	
SHRI Y. G. GOKHALE	Central Road Research Institute (CSIR),
	New Delhi
SHRI R. S. SHUKLA (Alternate)	
SHRI G. RAMAN,	Director General, BIS (Ex-officio Member)
Director (Civ Engg)	

Secretary

SHRI M. SADASIVAM
Assistant Director (Civ Engg), BIS

Indian Standard
**SPECIFICATION FOR
BITUMEN MASTIC FOR TANKING AND
DAMP-PROOFING**
(First Revision)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Bureau of Indian Standards on 30 June 1987, after the draft finalized by the Waterproofing and Damp-proofing Sectional Committee had been approved by the Civil Engineering Division Council.

0.2 Bitumen mastic has proved to be a suitable damp-proofing material for underground tanks, basements, etc. The inherent quality of mineral components and its binder to resist dampness, decay, bacterial contamination, weathering, etc, makes bitumen mastic suitable for use as a good damp-proofing material. This standard is intended to provide the required guidance in proportioning of bitumen and aggregates so as to get bitumen mastic for tanking, damp-proofing, etc. The choice of materials and proportioning aims at obtaining dense voidless mix to ensure imperviousness, the required flexibility of the mastic and the workability to ensure ease of application.

0.3 This standard was first published in 1970. The present revision incorporates the changes necessary due to developments and revision of other standards referred to in the standard. In this revision, use of carbon tetrachloride and trichloroethylene have been added in the physical properties of bitumen.

0.4 In the formulation of this standard, due weightage has been given to international co-ordination among the standards and practices prevailing in different countries in addition to relating it to the practices in the field in the country.

0.5 This standard is one of a series of Indian Standard specifications on materials for use in waterproofing and damp-proofing of buildings. Other specifications published so far in the series are:

IS : 1322-1982 Specification for bitumen felts for waterproofing
and damp-proofing (*third revision*)

IS : 1580-1969 Specification for bituminous compounds for waterproofing and caulking purposes (*first revision*)

IS : 3037-1986 Specification for bitumen mastic for use in waterproofing of roofs (*first revision*)

IS : 3384-1986 Specification for bitumen primer for use in waterproofing and damp-proofing (*first revision*)

0.6 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard covers the requirements for bitumen mastic used as covering material for damp-proofing of underground tanks, basements of buildings, water reservoirs, swimming pools, irrigation canals, etc.

2. TERMINOLOGY

2.1 For the purpose of this standard, the definitions given in IS : 334-1982† and IS : 4911-1968‡ shall apply.

3. GENERAL CHARACTERISTICS

3.1 The bitumen mastic shall consist of a mixture of bitumen, aggregates and mineral filler in suitable proportions so as to give it a semi-fluid consistency when heated to about 180°C. The mastic at this temperature shall be easily compressible by trowels into a compact and uniform layer.

4. MATERIALS

4.1 Bitumen — The physical properties of bitumen used shall conform to those specified in Table 1, when tested in accordance with the methods of tests specified therein.

*Rules for rounding off numerical values (*revised*).

†Glossary of terms relating to bitumen and tar (*second revision*).

‡Glossary of terms relating to bituminous waterproofing and damp-proofing of buildings.

TABLE 1 PHYSICAL PROPERTIES OF BITUMEN

(Clause 4.1)

Sl. No.	CHARACTERISTIC	REQUIREMENTS	METHOD OF TEST, REF TO
(1)	(2)	(3)	(4)
i)	Softening point (ring and ball method)	50 to 90°C	IS : 1205-1978 ¹
ii)	Penetration at 25°C in 1/100 cm	20 to 40	IS : 1203-1978 ²
iii)	Ductility at 27°C (<i>Min</i>) in cm	3	IS : 1208-1978 ³
iv)	Loss on heating, percent (<i>Max</i>)	1	IS : 1212-1978 ⁴
v)	Solubility in CS ₂ , percent (<i>Min</i>)	99	IS : 1216-1978 ⁵
	or Carbon tetrachloride or trichloroethylene		

NOTE — Paving bitumen of the grade S35 conforming to IS : 73-1961⁶ and industrial bitumen of the grade 65/25, conforming to IS : 702-1961⁷ are typical examples of binder which will satisfy the requirements of this table.

¹Determination of softening point.

²Determination of penetration.

³Determination of ductility.

⁴Determination of loss on heating.

⁵Determination of solubility in carbon disulphide or trichloroethylene.

⁶Specification for paving bitumen (*revised*).

⁷Specification for industrial bitumen (*revised*).

4.2 Filler — The filler shall be lime-stone powder passing 75-micron IS Sieve and shall have a calcium carbonate content of not less than 80 percent by weight, when determined in accordance with the method specified in Appendix A of IS : 1195-1978^{*}.

4.3 Aggregates — Fine aggregates shall only be used. Fine aggregate shall consist of naturally occurring sand or crushed lime-stone or crushed hard rock. The grading of the aggregate is given in Table 2 for guidance.

5. MANUFACTURE AND COMPOSITION

5.1 The filler and fine aggregate shall be mixed together and heated to a temperature of 190 to 205°C. The required quantity of bitumen

^{*}Specification for bitumen mastic for flooring (*second revision*).

shall be separately heated to 170 to 180°C and added to the aggregate. These shall be mixed and cooked in a mechanically agitated mastic cooker until the materials are thoroughly mixed. During mixing, care shall be taken to ensure that the contents in the cooker are at no time heated to a temperature exceeding 205°C. Mechanical cooker should be such that it can discharge whole of the mix in about 30 minutes time.

TABLE 2 GRADING OF FINE AGGREGATES

(Clause 4.3)

TYPE OF SIEVE USED [see IS : 460 (PART 1)-1985]	PERCENTAGE BY WEIGHT
Passing 75 micron IS Sieve	0 to 10
Retained on 75 micron IS Sieve and passing 212 micron IS Sieve	10 to 18
Retained on 212 micron IS Sieve and passing 600 micron IS Sieve	40 to 54
Retained on 600 micron IS Sieve and passing 2.36 mm IS Sieve	24 to 40
Retained on 2.36 mm IS Sieve	Nil

5.2 If the mastic has to be pre-manufactured in the factory, and be cast into blocks and then taken to site, the mastic shall be prepared as given in 5.2.1.

5.2.1 The filler and fine aggregates shall be properly mixed and heated to a temperature of 190 to 205°C. The required quantity of bitumen shall be separately heated to 170 to 180°C and added to the aggregate. These shall be mixed and cooked in a mechanically agitated mastic cooker, until the materials are thoroughly mixed. The mastic shall then be cast into blocks weighing about 25 kg.

5.2.2 When required, the bitumen mastic blocks shall be broken into convenient sizes, and remelted and mixed in the mastic cooker at the site of the work.

5.3 Composition — The composition of the bitumen mastic, when determined in the manner specified in Appendix C of IS : 1195-1978*, shall conform to the requirements given in Table 3.

*Specification for bitumen mastic for flooring (second revision).

TABLE 3 COMPOSITION OF BITUMEN MASTIC BY ANALYSIS

(Clause 5.3)

SL No.	REQUIREMENTS	PERCENTAGE BY WEIGHT TOTAL MASTIC
i)	Soluble bitumen	15 to 17
ii)	Aggregate passing 75-micron IS Sieve	42 to 52
iii)	Aggregate passing 212-micron IS Sieve and retained on 75-micron IS Sieve	3 to 10
iv)	Aggregate passing 600-micron IS Sieve and retained on 212-micron IS Sieve	15 to 25
v)	Aggregate passing 2.36 mm IS Sieve and retained on 600-micron IS Sieve	7 to 20
vi)	Aggregate retained on 2.36-mm IS Sieve	Nil

6. HARDNESS NUMBER

6.1 The hardness number of the bitumen mastic shall be between 20 and 50 at 25°C, when determined in the manner described in Appendix D of IS : 1195-1978*.

7. SAMPLING AND CRITERIA FOR CONFORMITY

7.1 During Discharge from Mixer — Three or more separate portions of not less than 5 kg each of bitumen mastic shall be taken at intervals during the discharge of the mixer. The specimen shall include portions taken at beginning or at the end of the discharge except in cases where the practice of returning to the mixer the first and last portions discharged is followed. The portions shall then be thoroughly mixed at a temperature of 190 to 205°C. The mixture shall be floated out on an iron plate with the aid of a wooden float to a thickness not less than 25 mm. While still warm, the specimen shall be loosened from the plate, and a representative portion weighting not less than 5 kg, shall be forwarded to the laboratory for examination.

7.2 Blocks — Material in block form shall be sampled by taking approximately equal amounts, in pieces, from not less than 6 blocks taken at random. The total specimen of not less than 5 kg, shall be forwarded to the laboratory for examination.

*Specification for bitumen mastic for flooring (second revision).

7.3 Criteria for Conformity — The bitumen mastic shall be considered as conforming to this specification if the requirements given in **5.3** and **6.1** are satisfied.

8. MARKING

8.1 If cast into blocks for storage the date of manufacture and name of the manufacturer shall be indicated suitably.

8.2 BIS Certification Marking

The product may also be marked with Standard Mark.

8.2.1 The use of the Standard Mark is governed by the provisions of Bureau of Indian Standards Act, 1986 and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 331 01 31, 331 13 75

Telegrams: Manaksanstha
(Common to all Offices)

Regional Offices:

	Telephone
Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002	{ 331 01 31 331 13 75 36 24 99
*Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola, CALCUTTA 700054	
Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036	{ 2 18 43 3 16 41 41 24 42 41 25 19 41 29 16
Southern : C. I. T. Campus, MADRAS 600113	
†Western : Manakalaya, E9 MIDC, Marol, Andheri (East), BOMBAY 400093	6 32 92 95

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMADABAD 380001	{ 2 63 48 2 63 49
‡Peenya Industrial Area 1st Stage, Bangalore Tumkur Road BANGALORE 560058	{ 38 49 55 38 49 56
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHCPAL 462003	6 67 16
Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002	5 36 27
53/5, Ward No. 29, R.G. Barua Road, 5th Byelane, GUWAHATI 781003	3 31 77
5-8-56C L. N. Gupta Marg (Nampally Station Road), HYDERABAD 500001	23 10 83
R14 Yudhister Marg, C Scheme, JAIPUR 302005	{ 6 34 71 6 98 32
117/418 B Sarvodaya Nagar, KANPUR 208005	{ 21 68 76 21 82 92
Patliputra Industrial Estate, PATNA 800013	6 23 05
T.C. No. 14/1421, University P.O., Palayam TRIVANDRUM 695035	{ 6 21 04 6 21 17

Inspection Offices (With Sale Point):

Pushpanjali, First Floor, 205-A West High Court Road, Shankar Nagar Square, NAGPUR 440010	2 51 71
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	5 24 35

*Sales Office in Calcutta is at 5 Chowringhee Approach, P. O. Princep Street, Calcutta 700072

†Sales Office in Bombay is at Novelty Chambers, Grant Road, 89 65 28
Bombay 400007

‡Sales Office in Bangalore is at Unity Building, Narasimharaja Square, 22 36 71
Bangalore 560002